



TECHNICAL DATA

SPAR VARNISH SPRAY #8040 GLOSS, #8042 SATIN & #8047 SEMI-GLOSS

DESCRIPTION

Recommended Uses:

Cabot Interior/Exterior Spar Varnish Spray provides maximum protection and long-lasting beauty to wood, metal and fiberglass surfaces. Dries hard overnight.

Composition:

Alkyd Resin

Finish:

Dries to a highly durable, protective, clear coat

Sheen Levels:

Gloss #8040, Satin #8042 and Semi-Gloss #8047

Coverage:

On smooth wood, approximately 10-30 square feet per 11.5-ounce container

Packaging/Containers:

11.5-ounce aerosol can

Restrictions:

DO NOT USE OVER PRODUCTS THAT CONTAIN STEARATES.

Do not apply when air or surface temperature is below 50°F.

Do not apply over wet or damp surfaces.

Do not apply this product adjacent to cement or stucco.

TECHNICAL DATA

Environmental Impact:

These products are in compliance with V.O.C. (Volatile Organic Compounds) requirements for Specialty Architectural Coatings under current regulations. Call Cabot's Technical Services & Support for additional information pertaining to current V.O.C. rulings.

Cleanup and Disposal: Clean valve by inverting can and pressing valve until gas comes out. **Never insert** sharp objects into opening at top of can.

Dispose of empty cans or unused portion in accordance with local, state and federal regulations. Close container when not in use. Material Safety Data Sheets (MSDS) are available upon request.

DANGER: Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after each use, place rags, steel wool or waste in a sealed, water-filled metal container and dispose of according to local regulations.

DANGER: CONTAINS ACETONE AND PETROLEUM DISTILLATES.

DO NOT SMOKE. Vapors may ignite explosively. Keep away from sparks, open flame and lit cigarettes. Turn off stoves, heaters, electric motors, pilot lights and other sources of ignition during use and until all vapors are gone. Prevent build up of vapors by opening all windows and doors for cross ventilation.

Storage: Contents under pressure. Extremely flammable.

Emergency Medical Telephone: 1-888-345-5732

Physical and Chemical Data:

Water Resistant: Yes

Drying Time: Dries hard overnight. Three (3) thin coats are recommended. Recoat within 1 hour or after 24 hours, otherwise coating may wrinkle or lift.

Weight Per Gallon: 6.05 - 6.15 pounds per gallon.

Flash Point: N/A

Film Thickness: (Dry) 0.5 - 1.0 mils per coat on sealed surfaces?

Shelf Life: A minimum of five (5) years in closed original containers.

% Solids (weight): 16.5 - 17.5

% Solids (volume): 12.5 - 13.0

% Pigment (weight): 0 - 0.6

Pigment Type: Precipitated Silica

Vehicle Type: Alkyd resin

Solvent Type: Ketones, Aliphatic and Aromatic Hydrocarbons

V.O.C. Content: GPL Maximum of 63.5-64.0% V.O.C and a maximum of 1.1 PWMIR.

SPAR VARNISH SPRAY
#8040 GLOSS, #8042 SATIN & #8047 SEMI-GLOSS

APPLICATION

Surface Preparation:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust.

LEAD IS TOXIC. Contact the USEPA/Lead Information Hotline at 1-800-424-LEAD (5323) or visit www.epa.gov/lead

Wood surfaces must be clean, free of sanding dust, wax, grease, old finishes, mildew stains or other contaminants. Surfaces must be absolutely dry with moisture levels reading below 15%. Fill all nail holes with high-quality wood putty. Sand the wood surface to the desired smoothness using progressively finer grades of sandpaper to remove all scratches and nicks. On previously clear-coated surfaces, make sure surface is in sound condition and polyurethane is compatible with surface. Lightly sand existing surface before applying first coat.

DIRECTIONS FOR USE WITH ADEQUATE VENTILATION:

1. Clean and dry surface. Remove dirt, grease, etc. Dull glossy surfaces.
2. Use outdoors or in a well-ventilated area when temperature is 65-90° F (18-32° C).
3. Cover nearby area to protect from spray mist.
4. Shake well for at least 1 minute listening for rattle of mixing ball. Shake frequently during application.
5. Hold can 8-10 inches from surface. Move can back and forth releasing button after each stroke. Overlap each stroke. Three (3) thin coats are recommended. Recoat within 1 hour or after 24 hours, otherwise coating may wrinkle or lift.
6. If spray button clogs, remove button from can and run knife-edge through slit at end of spray button stem. DO NOT insert pins or other sharp objects into valve opening of can.
7. To prevent clogging after use, turn can upside down and press spray head for 3 seconds.

Drying Time: Dries hard overnight. Recoat within 1 hour or after 24 hours, otherwise coating may wrinkle or lift. Poor ventilation, high humidity and low temperatures will lengthen dry time.

Number of Coats: Apply three thin coats to avoid over application.

AVAILABILITY

Cabot Wood Care Products are sold throughout the United States and Canada. For a list of Cabot dealer locations, please contact Cabot's Technical Services & Support at 1-800-US-STAIN.

WARRANTY

If this product does not perform as stated on the label after you apply it according to label directions, Cabot will either replace this product or refund its purchase price, at its option. Cabot disclaims all other implied or expressed warranties. Cabot will not provide or pay for labor for removal or application of the product. This warranty excludes all incidental or consequential damages. This warranty gives you specific legal rights, and you may have other rights which vary from state to state.

MAINTENANCE

Minimal because Cabot Spar Varnish Spray provides a tough, abrasion-and water-resistant finish.

TECHNICAL SERVICES

For additional technical information see your specialized Cabot dealer or call Cabot's Technical Services & Support toll-free at 1-800-US-STAIN (877-8246).

FILING SYSTEMS

For complete model specifications and technical data on all Cabot products, visit the Cabot Home Page at: cabotstain.com.



Cabot®
Newburyport, MA 01950
Tel.: 800-US-STAIN
Fax: 1-800-998-3299
cabotstain.com